(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 29 August 2002 (29.08.2002)

PCT

(10) International Publication Number WO 02/066404 A1

(51) International Patent Classification⁷: C07C 2/32, B01J 31/22

- (21) International Application Number: PCT/NL01/00149
- (22) International Filing Date: 22 February 2001 (22.02.2001)
- (25) Filing Language:

English

(26) Publication Language:

English

- (71) Applicant (for all designated States except US): STICHT-ING DUTCH POLYMER INSTITUTE [NL/NL]; Den Dolech 2, MA 1.13, NL-5612 AZ Eindhoven (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): DECKERS, Patrick, Josef, Wilhelmus [NL/NL]; Bankastraat 6, NL-9715 CA Groningen (NL). HESSEN, Bart [NL/NL]; Heideweg 10, NL-9824 TJ Norrdwijk (NL).
- (74) Agent: VAN DER KLOET-DORLEIJN, G., W., F.; Exter Polak & Charlouis B.V., P.O. Box 3241, NL-2280 GE Rijswijk (NL).

- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL., PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CATALYST SYSTEM FOR THE TRIMERISATION OF OLEFINS

(57) Abstract: The invention relates to a catalyst system for the selective trimerisation of olefins, which system is based on a titanium complex of formula $(Cp-B(R)_nAr)TiR^1_3$, wherein: Cp is a cyclopentadienyl type ligand, optionally substituted, B is a bridging group, based on a single atom selected from the groups 13 to 16 inclusive of the Periodic System, Ar is a aromatic group, optionally substituted, R is, independently, hydrogen, or a hydrocarbon residue, optionally being substituted adn optionally containing heteroatoms, or groups R and B are joined together to form a ring, n is an integer equal to the (valency of B minus 2), and R^1 is a mono-anionic group, and further comprises an activator. The present catalyst system obviates the use of toxic chromium compounds.

Title: Catalyst system for the trimerisation of olefins.

The invention relates to a catalyst system for the selective trimerisation of olefins, which system comprises a transition metal complex.

Such a catalyst for trimerisation of olefins is known from 5 EP-A-0608447 and consists of a combination of a metal source, a pyrrole containing compound and a metal alkyl in an electron donor solvent. The transition metal source consists of a chromium, nickel, cobalt, or iron compound, preferably a chromium compound is used.

Because chromium compounds are highly toxic, and therefore need 10 special handling precautions, a catalyst system for the trimerisation of olefins, which is not based on a chromium compound is needed.

A catalyst system has now been found which is not based on a chromium compound, but still shows a high selectivity in the trimerisation of olefins with respect to the trimerisation product.

- More specifically, the invention relates to a catalyst system as indicated above, which is characterized in that said catalyst comprises
 - a) a half-sandwich substituted cyclopentadienyl titanium complex of formula
- $(Cp-B(R)_nAr)TiR^{1}_{3}$

wherein

Cp is a cyclopentadienyl type ligand, optinally substituted, B is a bridging group, based on a single atom selected from the groups 13 to 16 inclusive of the Periodic System,

- 25 Ar is a aromatic group, optionally substituted,
 - R is, independently, hydrogen, or a hydrocarbon residue, optionally being substituted and optionally containing heteroatoms, or groups R and B are joined together to form a ring,
- n is an integer equal to the (valency of B minus 2), and \mathbb{R}^1 is a mono-anionic group, and
 - b) an activator.

It is observed that the catalyst system as disclosed in EP-A-0608447 is preferably a chromium catalyst, but a catalytic system 35 based on a titanium compound, more specifically TiO(acac)₂, was also

tested as a catalyst for the trimerisation of ethylene. The selectivity for hexene-1 was in that case nevertheless rather low. A high selectivity for hexene-1 is industrially very important because of the use of hexene-1 as starting material for the preparation of different kinds of (co)polymers.

It is further observed that trimerisation is in the abovementioned reference and in the present disclosure defined as the
combination of one or more kinds of olefins, wherein the number of
olefin, i.e. double, bonds is reduced by two. The term "trimerisation"

10 is thus intended to include "co-trimerisation". So, for example, the
number of olefin bonds in the combination of three ethylene units is
reduced by two, to one olefin bond, in 1-hexene.

A half-sandwich substituted cyclopentadienyl titanium complex as a catalyst, in the presence of a co-catalyst, is known for example 15 from Macromol. 1999, 32, 4491-4493. This titanium complex does nevertheless not have a bridging group in its structure; moreover, the catalyst system is used for the synthesis of polyethylenes containing significant amounts of butyl branches, and is thus used in a polymerisation process.

As is known from EP-A-0 780 353, the properties of a polymer do not change markedly with the addition or removal of one or a few repeating units, contrary to the properties of a product obtained by oligomerisation or trimerisation. A polymerisation catalyst thus results in completely different products than a trimerisation catalyst does.

Half-sandwich cyclopentadienyl titanium complexes of formula (CpB(R)₂Ar)TiMe₃ and (CpB(R)₂Ar)TiCl₃ are known per se from J. Saßmannshausen et al., J. Organomet. Chem. 1999, 592, 84-94. In these known complexes B(R)₂Ar can be CMe₂Ph, CHPh₂ or SiMe₂Ph. These complexes were only used as polymerization catalysts; there is no indication at all that these known catalysts could effectively be used for the selective trimerisation of olefins. On the contrary: it is said that the effect of a comparatively weakly coordinated pendant ligand, such as phenyl, on the behaviour of a polymerisation catalyst is difficult to predict. Moreover, a possible favourable effect of a catalyst having a bridging group only consisting of a single atom, for a trimerisation process of ethene to obtain hexene-1, is not mentioned or suggested in this reference.

As mentioned before, Cp is a cyclopentadienyl type ligand, 40 which is optionally substituted.

More preferably, Cp is a cyclopentadienyl, indenyl or fluorenyl group, which may be substituted or not with one to five (cyclopentadienyl), one to seven (indenyl) or one to nine (fluoranyl) substituent alkyl or silyl groups, especially methyl or trimethylsilyl groups.

In the catalyst system according to the invention Ar is an aromatic group, which is optionally substituted; examples thereof are phenyl, naphthalene, anthracene or phenanthrene. This enumeration is not to be regarded as limitative; other aromatic groups can also be

10 used, provided that a coordination complex, based on π -electrons of said group, together with titanium can be formed.

In a preferred embodiment of the invention, the catalyst system comprises a complex of the above given formula, wherein said group B consists of carbon or silicon,

- 15 Ar is phenyl, optionally substituted or being part of a larger aromatic entity,
 - R¹ is a halide, or mono-anionic hydrocarbon residue optionally containing heteroatoms, and
 - n is 2, then R is a mono-anionic hydrocarbon residue, optionally containing heteroatoms, or
 - n is 1, then R is a di-anionic hydrocarbon residue, optionally containing heteroatoms.

More preferably the catalyst system of the invention comprises a titanium complex of the above given formula, wherein

- 25 Ar is a phenyl group, substituted or not at the meta-or paraposition(s),
 - B is based on a carbon atom.

20

- n is 2, then groups R are, independently, methyl, or ethyl; or
- n is 1, then group R is $=CH_2$, or forms when R is C_4H_8 or C_5H_{10}
- 30 together with group B a diamionic cyclic group,
 - Cp is C_5H_4 or C_5H_3 (SiMe₃), and
 - R¹ is chlorine, methyl, or benzyl.

The half-sandwich, substituted cyclopentadienyl titanium complex, forming a part of the present catalyst system, is in a 35 preferred embodiment supported by a carrier. This carrier consists expediently either of a metal oxide, which is selected from the group consisting of alumina, boria, magnesia, thoria, zirconia, silica, or mixtures thereof, or it consists of a polymeric material.

As indicated above, the present catalyst system comprises an activator. Said activator is preferably methylalumoxane, a salt of a non-coordinating anion, or a Lewis acid capable of abstracting an anion from said transition metal complex and thus generating a cationic transition metal species with a non-coordinating anion.

An example of a salt of a non-coordinating anion is N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate, while such a Lewis acid is for example $B(C_6F_5)_3$. It is in this respect observed that any activator can be used provided that it is able to generate a cationic transition metal species with a non-coordinating anion. The term "non-coordinating anion" is meant to indicate the anionic part or derivative of the activator, which not or only weakly coordinates to the cationic form of the present catalyst.

Preferably the activator is methylalumoxane (also known as $15\,$ MAO). The molar ratio of Ti:Al is expediently from 1:100 to 1:1000.

The present catalyst system can further also comprise a scavenger. Examples of a scavenger are $i\text{-Bu}_3\text{Al}$ and $(i\text{-Bu}_2\text{Al})_2\text{O}$. A scavenger is normally used to scavenge impurities from the polymerisation medium to obtain a high productivity.

The invention further relates to a process to trimerize olefinic compounds which comprises carrying out said trimerisation in the presence of a catalyst system, as described above, under trimerisation conditions. Such a trimerisation als comprises cotrimerisation according to the definition given before.

The olefin to be trimerized is preferably selected from C_2 - C_{20} olefins or mixtures of two or more of these olefins. The preferred olefins are ethylene and 1-butene, more preferably ethylene.

The temperature is preferably in the range of from $20-150\,^{\circ}\text{C}$, at a pressure in the range of from 1,5 to 3 MPa.

The invention will further be explained in the following examples.

Experimental section

General considerations

All experiments were performed under a nitrogen atmosphere using standard Schlenk and glovebox techniques. Deuterated solvents (Aldrich, Acros) were dried over Na/K alloy and vacuum transferred before use. Cyclooctane (Aldrich, used as internal standard) was distilled from Na prior to use. Toluene (Aldrich, anhydrous, 99,8%)

was passed over columns of Al₂O₃ (Fluka), BASF R3-11 supported Cu oxygen and molecular sieves (Aldrich, 4Å). Diethyl ether and THF (Aldrich) were dried over Al₂O₃ (Fluka) and the other solvents (Aldrich) were dried over molecular sieves (Aldrich, 4Å). Ethene (AGA polymer grade) was passed over BASF R3-11 supported Cu oxygen scavenger and molecular sieves (Aldrich, 4Å).

The compounds 6,6-pentamethylenefulvene, C₅H₅CH₂Ph,
(C₅H₄C(=CH₂)Ph)Li, (C₅H₄CMe₂Ph)TiCl₃ (the catalyst used in
Example 1), (C₅H₄SiMe₂Ph)TiCl₃ (the catalyst used in Example 3),

(C₅H₄CMe₂-3,5-MeC₆H₃)TiCl₃ (the catalyst used in Example 2) and
B(C₆F₅)₃ were prepared according to procedures known as such. 6,6Diethylfulvene was prepared analogously to 6,6-pentamethylenefulvene
from cyclopentadiene and 3-pentanone. (C₅H₄CMe₂Ph)TiMe₃ (used in
Examples 10 and 11) was prepared through modification of a known
procedure by reaction of (C₅H₄CMe₂Ph)TiCl₃ with either Me₂Mg or
MeMgI. The preparations of other titanium complexes are disclosed
hereafter in the Preparation Examples A to F.

A toluene solution of MAO (26 wt%, Akzo Nobel Chemicals), MAO supported on silica (5 wt%, Witco) and [PhNMe $_2$ H][B(C $_6$ F $_5$) $_4$].(Akzo 20 Nobel Chemicals) were used as such.

NMR spectra were recorded on Varian Gemini 200/300 and Unity 500 spectrometers.

The ¹H NMR spectra were referenced to resonances of residual protons in the deuterated solvents. Chemicals shifts (δ) are given relative to tetramethylsilane (downfield shifts are positive). GC analyses were performed on a HP 6890 instrument equipped with a HP-1 dimethylpolysiloxane column (19095 Z-123). GC-MS analyses were conducted using a HP 5973 mass-selective detector attached to a HP 6890 GC instrument. Elemental analyses are the average of a least two independent determinations.

Preparation example A

Preparation of $(C_5H_4CH_2Ph)$ TiCl₃, to be used in Example 4. a) Preparation of $(C_5H_4CH_2Ph)$ Li

To a solution of 11.3 mmol n-BuLi in 30 ml of diethyl ether/hexane at -40 °C, 1.87 g (12.0 mmol) of CpHCH₂Ph [2] was added dropwise. The reaction mixture was allowed to warm to room temperature and stirred overnight. The solvents were removed in

vacuo. The white residue was stripped with pentane. After rinsing with 3x 10 ml of pentane and after drying in vacuo 1.55 g (9.6 mmol, 85%) of a white solid was isolated. - 1 H NMR (300 MHz, THF- d_8): δ 8.04-7.92 (m, 4H, Ph o- and m-H), 7.82 (m, 1H, Ph p-H), 6.33 (t, 3 J_{HH} 5 = 2.6 Hz, 2H, Cp), 6.29 (t, 3 J_{HH} = 2.6 Hz, 2H, Cp), 4.61 (s, 2H, CH₂) - 13 C NMR (75.4 MHz, THF- d_8): δ 148.2 (Ph C ipso), 130.5 (Ph o- or m-CH), 129.5 (Ph o- or m-CH), 126.3 (Ph p-CH), 120.0 (Cp C ipso), 105.1 (Cp CH), 103.9 (Cp CH), 39.0 (CH₂)

b) Preparation of (C5H4CH2Ph)TiCl3

To a solution of 1.42 g (8.8 mmol) (CpCH₂Ph)Li in 40 ml of methylene chloride, cooled at -40 °C, 0.96 ml (1.7 g, 8.9 mmol) titanium(IV) chloride was added. The reaction mixture was stirred at ambient temperatures overnight. The methylene chloride was removed in vacuo and the green-brown residue was stripped with pentane. After extraction with toluene, the extract was evaporated in vacuo and the extract residue was dissolved in methylene chloride. Brown crystals were obtained after cooling to -40 °C. Yield: 1.58 g (5.1 mmol, 58%) - ¹H NMR (300 MHz, C₆D₆): δ 7.09-7.03 (m, 3H, Ph m- and p-H), 6.82 (m, 2H, Ph o-H), 5.98 (m, 4H, Cp), 3.71 (s, 2H, CH₂) - ¹³C NMR (75.4 MHz, C₆D₆): δ 142.9, 138.3 (Ph and Cp C ipso), 128.9, 127.2 (Ph CH, one signal overlapped by solvent), 123.6, 123.2 (Cp CH), 37.7 (CH₂) - Anal. Calcd for C₁₂H₁₁TiCl₃: C, 46.57; H, 3.58; Ti, 15.48. Found: C, 47.07; H, 3.75, Ti, 15.38.

25 Preparation example B

Preparation of $(C_5H_4CEt_2Ph)TiCl_3$, to be used in Example 5.

a) Preparation of C₅H₄ (TMS) CEt₂Ph

To a solution of 4.85 g (58 mmol) PhLi in 200 ml of diethyl ether, cooled at -50 °C, 8.0 g (60 mmol) of 6,6-diethyl fulvene [1] 30 was added dropwise. The reaction mixture was allowed to warm to room temperature and was stirred for 3 hours. After 3 hours the yellow solution was cooled with an ice bath and 7.6 ml (6.5 g, 60 mmol) of trimethylsilyl chloride was added dropwise. The mixture was allowed to warm to room temperature and stirred overnight. The reaction 35 mixture was poured into 250 ml of ice water. The water layer was extracted with 2x 100 ml of light petroleum, after which the combined organic layers were rinsed with 200 ml of brine. The organic phase was dried on MgSO4. After evaporating the low-boiling volatiles in vacuo, the residue was distilled using a Kogelruhr-apparatus. The

product distilled at 110 °C at 0.5 mm Hg as a mixture of isomers. Yield: 9.21 g (32 mmol, 55%) - 1 H NMR (300 MHz, CDCl₃, main isomer): δ 7.28 (m, 4H, Ph o- and m-H), 7.18 (m, 1H, Ph p-H), 6.40 (m, 1H, C₅H₄), 6.31 (s, 1H, C₅H₄), 6.22 (m, 1H, C₅H₄), 3.27 (s, 1H, C₅H₄), 2.02 (m, 4H, C-CH₂-CH₃), 0.72 (m, 6H, C-CH₂-CH₃), 0.06 (s, 9H, TMS) b) Preparation of (C₅H₄CEt₂Ph)TiCl₃

To a solution of 6.30 g (22 mmol) of A.1 in 40 ml of methylene chloride, cooled at -40 °C, 2.45 ml (4.2 q, 22 mmol) of titanium chloride was added. The mixture was allowed to warm to room 10 temperature and stirred overnight. The methylene chloride was removed in vacuo and the residue was stripped with pentane. Extraction with methylene chloride and cooling to -60 °C afforded red-brown crystals of the title compound. Yield: 5.63 g (15.3 mmol, 70%) - ^{1}H NMR (300 MHz, C_6D_6): δ 7.24 (d, $^3J_{HH}$ = 7.3 Hz, 2H, Ph o-H), 7.17 (t, $^3J_{HH}$ = 7.3 15 Hz, 2H, Ph m-H), 7.06 (t, ${}^{3}J_{HH} = 7.3$ Hz, 1H, Ph p-H), 6.26 (t, ${}^{3}J_{HH} =$ 2.8 Hz, 2H, Cp), 6.04 (t, $^{3}J_{HH}$ = 2.8 Hz, 2H, Cp), 2.06 (m (dq), 2H, C- $\underline{\text{CH}}_2$ -CH₃), 1.86 (m (dq), 2H, C- $\underline{\text{CH}}_2$ -CH₃), 0.51 (t, ${}^3J_{\text{HH}}$ = 7.3 Hz, 6H, C- CH_2-CH_3) - ¹³C NMR (75.4 MHz, C_6D_6): δ 154.8 (Ph C *ipso*), 142.1 (Cp C ipso), 128.8 (Ph o-CH), 128.3 (Ph m-CH, overlap with solvent), 127.2 20 (Ph p-CH), 123.1, 121.8 (Cp CH), 48.6 ($\underline{C}(C_2H_5)_2$ ipso), 29.3 (C- \underline{CH}_2 - $\text{CH}_3)\,,~8.5~\text{(C-CH}_2\text{-CH}_3)$ - Anal. Calcd for $\text{C}_{16}\text{H}_{19}\text{TiCl}_3\colon$ C, 52.57; H, 5.24. Found: C, 52.75; H, 5.27.

Preparation example C

25 Preparation of {CpC[(CH₂)₅]Ph}TiCl₃, to be used in Example 6
a) Preparation of C₅H₄(TMS)C[(CH₂)₅]Ph

To a solution of 4.00 g (48 mmol) PhLi in 200 ml of diethyl ether, cooled at -50 °C, 6.95 g (48 mmol) of 6,6pentamethylenefulvene [1] was added dropwise. The reaction mixture

30 was allowed to warm to room temperature and was stirred for 3 hours. After 3 hours the yellow solution was cooled with an ice bath and 6.4 ml (5.5 g, 51 mmol) of trimethylsilyl chloride was added dropwise. The mixture was allowed to warm to room temperature and stirred overnight. The reaction mixture was poured into 250 ml of ice water.

35 The water layer was extracted with 2x 100 ml of light petroleum, after which the combined organic layers were rinsed with 200 ml of brine. The organic phase was dried on MgSO4. After evaporating the low-boiling volatiles in vacuo, the residue was distilled using a

Kogelruhr-apparatus. The product distilled at 165 °C at 0.4 torr as a mixture of isomers. Yield: 8.96 g (30 mmol, 63%) - 1 H NMR (300 MHz, CDCl₃, main isomer): δ 7.40 (m, 2H, Ph o-H), 7.33 (m, 2H, PH m-H), 7.15 (m, 1H, Ph p-H), 6.43 (m, 2H, C₅H₄), 6.15 (s, 1H, C₅H₄), 3.27 (s, 1H, C₅H₄), 2.17 (m, 4H, α -CH₂), 1.65-1.40 (m, 6H, β - and γ -CH₂), -0.03 (s, 9H, TMS)

b) Preparation of {C₅H₄C[(CH₂)₅]Ph}TiCl₃

Titanium chloride (1.4 ml, 2.4 q, 12.7 mmol) was added to a solution of 3.70 g (12.5 mmol) of $C_5H_4(TMS)C[(CH_2)_5]$ Ph in 40 ml of 10 methylene chloride, cooled at -40 °C. The reaction mixture was allowed to warm to room temperature and was stirred overnight. The methylene chloride was removed in vacuo and the residue was stripped with pentane. The residue was extracted with methylene chloride. Crystallization from a 1:1 mixture of CH2Cl2:pentane afforded red-15 brown crystals of the desired compound in 78% yield (3.68 q, 9.7 mmol). - ¹H NMR (300 MHz, C_6D_6): δ 7.16-7.06 (m, 4H, Ph o- and m-H), 7.01 (m, 1H, Ph p-H), 6.31 (t, ${}^{3}J_{HH} = 2.8 \text{ Hz}$, 2H, Cp), 5.97 (t, ${}^{3}J_{HH} =$ 2.8 Hz, 2H, Cp), 2.45 (d, $^{2}J_{HH} = 13.2$ Hz, 2H, α -CH₂ (eq)), 1.88 (m, 2H, α -CH₂ (ax)), 1.37 (br, 3H, β - and γ -CH₂), 1.25-1.05 (m, 3H, β - and 20 γ -CH₂) - ¹³C NMR (75.4 MHz, C₆D₆): δ 156.0 (Ph C ipso), 142.1 (Cp C ipso), 129.2 (Ph o-CH), 127.9 (Ph m-CH), 126.8 (Ph p-CH), 123.2, 120.9 (Cp CH), 45.1 ($C[(CH_2)_5]$ ipso), 35.8 (α -CH₂), 26.1 (γ -CH₂), 22.4 $(\beta-CH_2)$ - Anal. Calcd for $C_{17}H_{19}TiCl_3$: C, 54.08; H, 5.07; Ti, 12.69. Found: C, 53.93; H, 4.90; Ti, 12.62.

Preparation example D

25

Preparation of [C₅H₄C(=CH₂)Ph]TiCl₃, to be used in Example 7

To a solution of 0.61 ml (1.06 g, 5.6 mmol) titanium chloride in 40 ml of methylene chloride, cooled at -50 °C, 1.80 g (5.6 mmol) $[C_5H_4C(=CH_2)Ph]$ Li was added. The reaction mixture was allowed to warm to room temperature and was stirred overnight. The volatiles were removed in vacuo and the green-black residue was stripped with pentane. Extraction with pentane afforded small analytically pure amounts of the desired compound. - 1H NMR (300 MHz, C_6D_6): δ 7.2-7.05 (m, 5H, Ph), 6.35 (t, $^3J_{HH}$ = 2.7 Hz, 2H, Cp), 6.01 (t, $^3J_{HH}$ = 2.7 Hz, 2H, Cp), 5.58 (s, 1H, =CH₂), 5.20 (s, 1H, =CH₂) - ^{13}C NMR (75.4 MHz, C_6D_6): δ 142.5 (Ph C ipso), 139.7 (Cp C ipso), 139.6 ($\underline{C}(=CH_2)$ ipso), 128.8, 128.7, 128.5 (Ph CH), 123.4, 121.1 (Cp CH), 120.5 ($C(=CH_2)$ -

Anal. Calcd for $C_{13}H_{11}TiCl_3$: C, 48.57; H, 3.45; Ti, 14.90. Found: C, 48.71; H, 3.55; Ti, 14.78.

Preparation Example E

5 Preparation of C₅H₃(3-SiMe₃)CMe₂Ph]TiCl₃, to be used in Example 8

a) Preparation of C₅H₃(SiMe₃)₂CMe₂Ph

To a solution of 2.25 g (11.8 mmol) (C₅H₄CMe₂Ph)Li [5] in 50 ml of diethyl ether and 20 ml of THF, cooled in ice water, 1.5 ml (1.3 g, 11.9 mmol) TMSCl was added dropwise. The mixture was allowed to warm to room temperature and was stirred overnight. The yellow solution was cooled in ice water and 4.8 ml (12 mmol) of a 2.5M n-BuLi solution in hexanes was added. After warming up to room temperature the mixture was stirred for 4 hours. The white suspension was cooled in ice water and 1.6 ml (1.4 g, 12.7 mmol) TMSCl was added dropwise. The mixture was allowed to warm to room temperature and stirred overnight. The yellow suspension was poured into 125 ml ice water. The water layer was extracted with 50 ml of light petroleum and the combined organic layers were dried on MgSO₄. After evaporation of low-boiling volatiles, the residue was distilled using a Kogelruhr-apparatus. The product distilled at 115 °C at 0.8 Torr.

- Yield: 2.87 g (8.7 mmol, 74%) 1 H NMR (200 MHz, CDCl₃): δ 7.4-7.1 (m, 5H, Ph), 6.40 (d, 3 J_{HH} = 2.2 Hz, 2H, Cp), 6.20 (t, 3 J_{HH} = 2.1 Hz, 1H, Cp), 1.53 (s, 6H, CMe₂), -0.03 (s, 18H, TMS) b) Preparation of [C₅H₃(3-SiMe₃)CMe₂Ph]TiCl₃
- To a solution of 0.92 ml (1.6 g, 8.4 mmol) TiCl₄ in 50 ml of methylene chloride, cooled at -50 °C, 2.75 g (8.4 mmol) of C₅H₃(SiMe₃)₂CMe₂Ph was added. The reaction mixture was allowed to warm to room temperature and was stirred overnight. The volatiles were removed in vacuo and the residue was stripped with pentane.
- 30 Extraction with methylene chloride and cooling down to -60 °C afforded 2.76 g (6.7 mmol, 80%) of the desired compound. 1 H NMR (300 MHz, C_6D_6): δ 7.1-6.85 (m, 5H+1H, Ph+Cp), 6.57 (m, 1H, Cp), 6.53 (m, 1H, Cp), 1.63 (s, 6H, CMe₂), 0.12 (s, 9H, TMS) 13 C NMR (75.4 MHz, C_6D_6): δ 158.5 (Ph C ipso), 148.5 (Cp C ipso), 144.1 (Cp C(TMS)
- 35 ipso), 128.7, 128.6, 126.7, 126.1, 124.6 (Ph+Cp CH), 41.2 (CMe₂
 ipso), 29.3, 29.0 (CMe₂), -0.8 (TMS) Anal. Calcd for C₁₇H₂₃SiTiCl₃:
 C, 49.84; H, 5.66; Ti, 11.69. Found: C, 49.70; H, 5.68; Ti, 11.59.

Preparation example F Preparation of $[C_5H_3(3-SiMe_3)CMe_2-3,5-Me_2C_6H_3]TiCl_3$, to be used in Example 9

a) Preparation of C₅H₃ (SiMe₃)₂CMe₂-3,5-Me₂C₆H₃

- To a solution of 1.15 g (5.3 mmol) [CpCMe $_2$ -3,5-Me $_2$ C $_6$ H $_3$]Li in 50 ml of diethyl ether, cooled with ice water, 0.7 ml (0.6 g, 5.5 mmol) trimethylsilyl chloride was added dropwise. The reaction mixture was allowed to warm to room temperature and was stirred overnight. The white suspension was cooled to -30 °C and 5.4 mmol of a 2.5M solution
- 10 of n-BuLi in hexanes was added dropwise. After stirring for 3 hours at ambient temperature, the reaction vessel was placed in ice water and 0.8 ml (0.7 g, 6.4 mmol) trimethylsilyl chloride was added. The reaction mixture was allowed to warm up to room temperature and was stirred overnight. The mixture was poured into 100 ml of ice water.
- 15 The water layer was extracted twice with 50 ml portions of light petroleum, and the combined organic layers were dried over MgSO₄. Kogelruhr-distillation at 160 °C and 0.4 Torr yielded 1.26 g (3.5 mmol, 66%) of the title compound 1 H NMR (200 MHz, CDCl₃): δ 6.90 (s, 2H, Ar o-H), 6.78 (s, 1H, Ar p-H), 6.37 (m, 2H, Cp), 6.19 (m, 1H,
- 20 Cp), 2.24 (s, 6H, ArMe), 1.51 (s, 6H, CMe₂), -0.05 (s, 18H, TMS) b) Preparation of $[C_5H_3(3-SiMe_3)CMe_2-3,5-Me_2C_6H_3]TiCl_3$

To a solution of 0.35 ml (0.6 g, 3.2 mmol) titanium chloride in 40 ml of methylene chloride, cooled at -40 °C, 1.18 g (3.3 mmol) of C_5H_3 (SiMe₃)₂CMe₂-3,5-Me₂C₆H₃ was added dropwise. The reaction mixture 25 was allowed to warm to room temperature and was stirred overnight.

- The volatiles were removed in vacuo and the residue was stripped with pentane. Extraction with pentane yielded 1.02 g (2.3 mmol, 72%) of light-brown crystals. ^{1}H NMR (300 MHz, C_6D_6): δ 6.96 (m, 1H, Cp), 6.69 (s, 2H, Ar o-H), 6.64 (m, 1+1H, Cp + p-H), 6.55 (m, 1H, Cp),
- 30 2.08 (s, 6H, ArMe), 1.70 (s, 6H, CMe₂), 0.13 (s, 9H, TMS) ¹³C NMR (75.4 MHz, C₆D₆): δ 159.1 (Ar C *ipso*), 148.5 (Cp C *ipso*), 144.1 (Cp C(TMS) *ipso*), 137.9 (Ar m-C *ipso*), 128.8, 128.4, 127.8, 124.7 (Cp CH + Ar p-CH), 124.1 (Ar m-H), 41.2 (CMe₂ *ipso*), 29.3, 29.2 (CMe₂), 21.5 (ArMe), -0.9 (TMS)

35

Preparation example G

Preparation of (C₅H₄CMe₂Ph)Ti(CH₂Ph)₃, to be used in Example 10

To a stirred solution of 0.52 g of (C₅H₄CMe₂Ph)TiCl₃ (1.54 mmol) in 30 ml of diethyl ether, cooled at -40 °C, a solution of benzyl 5 magnesium bromide (4.62 mmol) in diethyl ether was added dropwise. The mixture was allowed to warm to room temperature and was stirred for 3 hours. The solvent was removed in vacuo. The red solid was extracted with pentane. Cooling to -40 °C yielded red crystals of the desired product (560 mg, 1.11 mmol, 72%) - 1H NMR (500 MHz, $C_6D_6):\ \delta$ 10 7.17-7.11 (m, 10H, Ph m-and o-H and Bz m-H), 7.02 (m, 1H, Ph p-H), 6.90 (t, ${}^{3}J_{HH}$ = 7.5 Hz, 3H, Bz p-H), 6.81 (d, ${}^{3}J_{HH}$ = 7.5 Hz, 6H, Bz o-H), 5.74 (ps. t, $^{3}J_{HH}$ = 2.8 Hz, 2H, Cp), 5.50 (ps. t, $^{3}J_{HH}$ = 2.8 Hz, 2H, Cp), 2.97 (s, 6H, Ti-CH₂), 1.38 (s, 6H, CMe₂) - 13 C-NMR (125.7) MHz, C_6D_6): δ 149.6 (s, Ph C ipso), 149.1 (s, Bz C ipso), 146.7 (s, Cp 15 C ipso), 128.8 (dd, $^{1}J_{CH}$ =158 Hz, Bz m-CH, overlap with solvent), 128.5 (d, $^{1}J_{CH}=151$ Hz, Ph m-CH, overlap with solvent), 127.0 (dm, $^{1}J_{CH}=161$ Hz, Bz o-CH), 126.5 (dm, ${}^{1}J_{CH}=156$ Hz, Ph o-CH), 126.4 (dm, ${}^{1}J_{CH}=156$ Hz, Ph p-CH), 123.0 (dt, ${}^{1}J_{CH}$ =160 Hz, Bz p-CH), 118.4 (dm, ${}^{1}J_{CH}$ =168 Hz, Cp CH), 113.5 (dm, ${}^{1}J_{CH}=172$ Hz, Cp CH), 93.5 (t, ${}^{1}J_{CH}=123$ Hz, Ti-CH₂), 20 40.5 (s, CMe_2), 30.2 (q, $^1J_{CH}$ =122 Hz, CMe_2) - Anal. Calcd for $C_{35}H_{36}Ti$: C, 83.32; H, 7.19; Ti, 9.49. Found: C, 82.63; H, 7.32; Ti, 9.35.

Example 1: Catalytic ethene conversion with (C5H4CMe2Ph)TiCl3/MAO

The reactions were performed in a stainless steel 1L autoclave 25 (Medimex), fully temperature and pressure controlled and equipped with solvent and catalyst injection systems. In a typical experiment, the autoclave was evacuated and heated for 45 min at 90 °C prior to use.

The reactor was then brought to the desired temperature,

30 charged with 200 ml of toluene and pressurized with ethene. After
equilibrating for 15 min, the appropriate amount of MAO/toluene was
injected together with 25 ml of toluene. Subsequently a mixture of
2.50 g cyclooctane (internal standard) and 1.0 ml (0.87 g) of a 15 mM
stock solution of the titanium complex in toluene was injected,

35 together with 25 ml of toluene, to start the reaction. During the run
the ethene pressure was kept constant to within 0.2 bar of the
initial pressure by replenishing flow. After the specified run time,
the reactor was vented and the residual MAO was destroyed by addition
of 20 ml of ethanol. Samples of the reaction mixture were taken to

analyze and quantify the soluble components. Polymeric product was stirred for 90 min in acidified ethanol and repeatedly rinsed with ethanol and light petroleum on a glass frit. The polymer was initially dried in air and subsequently in vacuo at 70 °C overnight.

The results of the catalytic experiments are summarized in Table 1 (ethene conversion with the $(C_5H_4CMe_2Ph)\,TiCl_3/MAO$ catalyst system) and Table 2 (ethene conversion with the $(C_5H_4CMe_2Ph)\,TiCl_3/MAO$ catalyst system).

In these experiments, the C₆ fraction consists predominantly of 1-hexene (99+ %), with traces of 2- and 3-hexenes. The only detectable product of the C₈ fraction is 1-octene. The C₁₀ fraction is a mixture of isomers with either vinyl (90%), vinylidene (5%) or internal olefinic (5%) unsaturation, and consists predominantly of 5-methylnon-1-ene (75-85%). Higher olefins (C₁₂-C₂₄) constitute less than 0.5 wt% of the total amount of product formed.

Table 1:

Test nr.	P(ethene) MPa	°C	C ₆ g (wt%)	Cg (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity $kg(C_6)$ $mol(Ti)^{-1} h^{-1}$
1	0.2	30	8.0 (87)	0.1 (0.8)	1.0 (11)	0.2 (1.6)	1066
2	0.5	30	20.9 (83)	0.3 (1.2)	3.5 (14)	0.5 (1.8)	2787
3	1.0	30	47.2 (86)	0.9 (1.6)	5.1 (9)	1.4 (2.6)	6292
4	0.5	50	12.4 (83)	0.2 (1.1)	1.6 (11)	0.7 (4.6)	1653
5	0.5	80	3.3 (76)	0.05(0.9)	0.2 (4)	0.8 (19)	440

20 Toluene solvent, 15 μmol Ti, Al:Ti = 1000, 30 min run time

Table 2:

25

Test nr.	Run time min	Al:Ti	C ₆ g (wt%)	Cs g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
6	15	1000	16.6 (89)	0.2 (1.0)	1.4 (8)	0.4 (2.2)	4413
7	30	1000	20.9 (83)	0.3 (1.2)	3.5 (14)	0.5 (1.8)	2787
8	60	1000	27.1 (80)	0.4 (1.2)	5.5 (16)	0.9 (2.7)	1809
9	30	500	15.2 (86)	0.2 (1.2)	1.8 (10)	0.5 (2.8)	2029

Toluene solvent, 15 µmol Ti, 30 °C, 0.5 MPa ethene

Comparative example A: Catalytic ethene conversion with $(C_5H_4CMe_3)$ TiCl $_3/MAO$

The general procedure and conditions of example 1 were followed, using the $(C_5H_4CMe_3)TiCl_3/MAO$ catalyst system. The results of the catalytic experiment are listed in Table 3.

Table 3:

Test	P(ethene)	T	C ₆	C ₈	C ₁₀	PE	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
nr.	MPa	°C	g (wt%)	g (wt%)	g (wt%)	g (wt%)	
a	0.5	30	0.5 (17)	0.1 (3)	0.1 (4)	2.4 (76)	72

5 Example 2: Catalytic ethene conversion with (C₅H₄CMe₂-3,5-Me₂C₆H₃)TiCl₃/MAO

The general procedure and conditions of example 1 were followed, using the $(C_5H_4CMe_2-3,5-Me_2C_6H_3)\,TiCl_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 4.

Table 4:

10

Test nr.	P(ethene) MPa	°C	C ₆ g (wt%)	g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity $kg(C_6)$ $mol(Ti)^{-1} h^{-1}$
10	0.5	30	7.9 (94)	0.02 (0.2)	0.4 (5)	0.1 (1.3)	1052
11	0.5	50	4.5 (93)	0.03 (0.6)	0.2 (4)	0.1 (2.1)	599

15 Example 3: Catalytic ethene conversion with $(C_5H_4SiMe_2Ph)TiCl_3/MAO$ The general procedure and conditions of example 1 were followed, using the $(C_5H_4SiMe_2Ph)TiCl_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 5. Higher olefins $(C_{12}-C_{24})$ are also formed, constituting about 8 wt% of the total amount of product formed.

Table 5:

25

Test nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	Cs g (wt%)	C ₁₀ g (wt%)	C ₁₂ -C ₂₄ g (wt%)	g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
12	0.5	30	2.1 (36)	0.3 (5)	0.4 (7)	0.5 (8)	2.6 (44)	284
13	0.5	50	2.6 (47)	0.4 (7)	0.4 (7)	0.4 (7)	1.7 (32)	352

Example 4: Catalytic ethene conversion with (C5H4CH2Ph)TiCl3/MAO

The general procedure and conditions of example 1 were followed, using the $(C_5H_4CH_2Ph)\,TiCl_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 6. Higher olefins 30 $(C_{12}-C_{24})$ are also formed, constituting about 9 wt% of the total amount of products formed.

Table 6:

Test nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	Cs g (wt%)	C ₁₀ g (wt%)	C ₁₂ -C ₂₄ g (wt%)	PE g (wt%)	Producti-vity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
14	0.5	30	2.7 (42)	0.4 (6)	0.6 (9)	0.6 (9)	2.2 (34)	361
15	0.5	50	3.0 (54)	0.3 (6)	0.5 (9)	0.5 (9)	1.2 (22)	405

5 Example 5: Catalytic ethene conversion with (C5H4CEt2Ph)TiCl3/MAO

The general procedure and conditions of example 1 were followed, using the $(C_5H_4CEt_2Ph)TiCl_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 7.

10 Table 7:

Test nr.	P(ethene) MPa	T °C	C ₆	C ₈ g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
16	0.5	30	18.5 (88)	0.05 (0.3)	1.4 (7)	1.0 (4.6)	2462
17	0.5	50	8.7 (84)	0.03 (0.3)	0.6 (5)	1.0 (9.9)	1159

Example 6: Catalytic ethene conversion with {CpC[(CH₂)₅]Ph}TiCl₃/MAO

The general procedure and conditions of example 1 were followed, using the $\{C_5H_4C[(CH_2)_5]Ph\}TiCl_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 8.

Table 8:

nr.	P(ethene) MPa	°C	C ₆ g (wt%)	Ca g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
18	0.5*	30	24.4 (87)	0.1 (0.3)	2.9 (10)	0.6 (2.0)	3248
19	0.5*	50	12.0 (86)	0.1 (0.4)	1.2 (9)	0.7 (5.2)	1593
20	0.5**	30	16.4 (91)	0.04 (0.2)	1.4 (8)	0.2 (1.3)	4362

^{* 30} min run time, ** 15 min run time

Example 7: Catalytic ethene conversion with $[C_5H_4C(=CH_2)Ph]TiCl_3/MAO$

The general procedure of example 1 was followed, using the $[C_5H_4C(=CH_2)Ph]TiCl_3/MAO$ catalyst system. The conditions and results of the catalytic experiments are listed in Table 9.

Table 9: Catalytic ethene conversion with the [C₅H₄C(=CH₂)Ph]TiCl₃/MAO

30 system (toluene solvent, 15 μ mol Ti, Al:Ti = 1000, 30 min run time)

Test nr.	P(ethene) MPa	r °C	G (Mt#)	Ca g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
21	0.5	30	17.3 (88)	0.1 (0.3)	1.4 (7)	0.9 (4.7)	2307
22	0.5	50	10.9 (86)	0.03(0.2)	0.7 (6)	1.1 (8.3)	1449

Example 8: Catalytic ethene conversion with $[C_5H_3(3-SiMe_3)CMe_2Ph]-TiCl_3/MAO$

The general procedure and condictions of example 1 were followed, using the $[C_5H_3(3-SiMe_3)CMe_2Ph]TiCl_3/MAO$ catalyst system. 5 The results of the catalytic experiments are listed in Table 10.

Table 10:

Test nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	Ca g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity $kg(C_6)$ $mol(Ti)^{-1} h^{-1}$
23	0.5	30	25.2 (85)	0.6 (2.1)	3.3 (11)	0.4 (1.2)	3357
24	0.5	50	20.1 (84)	0.4 (1.5)	3.3 (14)	0.3 (1.3)	2683
25	0.5	80	8.0 (88)	0.1 (1.4)	0.8 (8)	0.2 (2.1)	1069

10

Example 9: Catalytic ethene conversion with $[C_5H_3(3-SiMe_3)CMe_2-3,5-Me_2C_6H_3]TiCl_3/MAO$

The general procedure and conditions of example 1 were followed, using the [Cp(TMS)CMe₂-3,5-Me₂C₆H₃]TiCl₃/MAO catalyst

15 system. The results of the catalytic experiments are listed in Table

11. For the run at 30°C, the C₆ fraction consists of 99.9% 1-hexene, and the C₁₀ fraction of 94% 5-methylnon-1-ene.

Table 11:

20

Test	P(ethene)	T	C ₆	C ₈	C10	PE	Productivity
nr.	МРа	°C	g (wt%)	g (wt%)	g (wt%)	g (wt%)	kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
26	0.5	30	40.1 (84)	0.1 (0.2)	7.0 (15)	0.3 (0.6)	5347
27	0.5	50	25.7 (82)	0.1 (0.3)	4.8 (15)	0.6 (1.9)	3427

Example 10: Catalytic ethene conversion with (C₅H₄CMe₂Ph)Ti(CH₂Ph)₃/MAO

The general procedure and conditions of example 1 were followed, using the $(C_5H_4CMe_2Ph)$ Ti $(CH_2Ph)_3/MAO$ catalyst system. The results of the catalytic experiments are listed in Table 12.

Table 12:

		١	

Test nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	C ₈ g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
28	0.5	30	23.8 (82)	0.3 (1.1)	4.6 (16)	0.5 (1.6)	3175
29	0.5	50	18.6 (78)	0.3 (1.1)	4.0 (17)	0.8 (3.3)	2480

Example 11: Catalytic ethene conversion with $(C_5H_4CMe_2Ph)TiMe_3/MAO$ The general procedure and conditions of example 1 were followed, using the $(C_5H_4CMe_2Ph)TiMe_3/MAO$ catalyst system. The results of the catalytic experiment are listed in Table 13.

Table 13:

5

Test nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	C ₈ g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
30	0.5	30	25.7 (81)	0.4 (1.2)	5.2 (16)	0.5 (1.5)	3428
31	0.5	50	18.1 (79)	0.2 (1.0)	3.8 (17)	0.7 (3.2)	2412

10 Example 12: Catalytic ethene conversion with (C₅H₄CMe₂Ph)TiMe₃/MAO/SiO₂

The reaction was performed in a stainless steel 1 l autoclave (Medimex), fully temperature and pressure controlled and equipped with solvent and catalyst injection systems. Prior to use the 15 autoclave was preheated in vacuo for 45 min at 90 °C. The reactor was cooled to 30 °C, charged with 200 ml of toluene and pressurized with ethene. After equilibrating for 15 min, a slurry of 2.05 q of 5 wt% MAO/SiO₂ in 10 ml of toluene was injected together with 30 ml of toluene. Subsequently a mixture of 2.50 g cyclooctane (internal 20 standard) and 1.0 ml (0.87 g) of a 15 mM stock solution of $(C_5H_4CMe_2Ph)$ TiMe₃ in toluene was injected, together with 25 ml of toluene, to start the reaction. During reaction the ethene pressure was kept constant to within 0.2 bar of the initial pressure by replenishing flow. After 30 min the reactor was vented and the 25 remaining residual MAO was destroyed by addition of 20 ml of ethanol. Samples of the reaction mixture were taken to analyze and quantify the soluble components. The solids (polyethene and silica support) were stirred in acidified ethanol for 90 min and rinsed repeatedly with ethanol and light petroleum on a glass frit. The material was 30 dried in air overnight and subsequently in vacuo at 70 °C overnight, yielding 1.7 g of which the polyethene fraction was not determined. The results of the catalytic experiment are listed in Table 14; the conditions were: toluene solvent, 15 μ mol Ti, Al:Ti = 250, 30 min run time. Weight percentages calculated on C6-C10 products only.

Table 14:

Test	P(ethene)	T	C ₆	C _i	C ₁₀	PE	Productivit kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
nr.	MPa	°C	g (wt%)	g (wt%)	g (wt%)	g (wt%)	
32	0.5	30	13.8 (95)	0.1 (0.8)	0.6 (4)	n.d.	1837

5 Example 13: Catalytic ethene conversion with (C₅H₄CMe₂Ph)TiMe₃/[PhNMe₂H][B(C₆F₅)₄]

The reactions were performed in a stainless steel 500 mL autoclave (Medimex), fully temperature and pressure controlled and equipped with solvent and catalyst injection systems. Prior to use 10 the autoclave was preheated in vacuo for 45 min at 90 °C. The reactor was cooled to the desired temperature, charged with 150 ml of toluene and pressurized with ethene. After equilibrating for 15 min, a suspension of 16.5 μ mol [PhNMe₂H][B(C₆F₅)₄] in 5 ml of toluene was injected together with 25 ml of toluene. Subsequently a mixture of 15 2.50 g cyclooctane (internal standard) and 1.0 ml (0.87 g) of a 15 mM stock solution of the titanium trimethyl complex in toluene was injected, together with 25 ml of toluene, to start the reaction. During reaction the ethene pressure was kept constant to within 0.2 bar of the initial pressure by replenishing flow. After the desired 20 run time, the reactor was vented and samples of the reaction mixture were taken to analyze and quantify the soluble components. The polymer was repeatedly rinsed with ethanol and light petroleum on a glass frit. The polymer was dried in air overnight and subsequently dried in vacuo at 70 °C overnight. The results of the catalytic 25 experiments are listed in Table 15. The conditions were: toluene solvent, 15 μmol Ti, B:Ti = 1.1, 30 min run time

Table 15:

Test nr.	P(ethene) MPa	°C	C ₆ g (wt%)	Ca g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity kg(C ₆) mol(Ti) ⁻¹ h ⁻¹
33	0.5	30	14.6 (90)	0.2 (1.3)	1.2 (7)	0.3 (2.0)	1948
34	0.5	50	14.0 (82)	0.2 (1.1)	2.2 (13)	0.6 (3.4)	1867

Example 14: Catalytic ethene conversion with (C₅H₄CMe₂Ph)TiMe₃/B(C₆F₅)₃

The reaction was performed in a stainless steel 500 mL autoclave (Medimex), fully temperature and pressure controlled and equipped with solvent and catalyst injection systems. Prior to use the autoclave was preheated in vacuo for 45 min at 90 °C. The reactor

was cooled to the desired temperature, charged with 150 ml of toluene and pressurized with ethene. After equilibrating for 15 min, 1.0 ml (0.87 g) of a 16.5 mM stock solution of $B(C_6F_5)_3$ in toluene was injected together with 25 ml of toluene. Subsequently a mixture of 5 2.50 g cyclooctane (internal standard) and 1.0 ml (0.87 g) of a 15 mM stock solution of the titanium trimethyl complex in toluene was injected, together with 25 ml of toluene, to start the reaction. During reaction the ethene pressure was kept constant to within 0.2 bar of the initial pressure by replenishing flow. After the desired 10 run time, the reactor was vented and samples of the reaction mixture were taken to analyze and quantify the soluble components. The polymer was repeatedly rinsed with ethanol and light petroleum on a glass frit. The polymer was dried in air overnight and subsequently dried in vacuo at 70 °C overnight. The results of the catalytic 15 experiment are listed in Table 16. The conditions were: toluene solvent, 15 μ mol Ti, B:Ti = 1.1, 30 min run time.

Table 16:

nr.	P(ethene) MPa	T °C	C ₆ g (wt%)	C ₈ g (wt%)	C ₁₀ g (wt%)	PE g (wt%)	Productivity $kg(C_6)$ $mol(Ti)^{-1} h^{-1}$
35	0.5	30	5.8 (88)	0.1 (0.9)	0.3 (5)	0.4 (6.6)	776

CLAIMS

 A catalyst system for the selective trimerization of olefins comprising a transition metal complex characterized in that said catalyst comprises

 a half-sandwich substituted cyclopentadienyl titanium complex of formula

 $(Cp-B(R)_nAr)TiR^{1}_{3}$

wherein

5

10

15

Cp is a cyclopentadienyl type ligand, optinally substituted,

B is a bridging group, based on a single atom selected from the groups 13 to 16 inclusive of the Periodic System,

Ar is a aromatic group, optionally substituted,

R is, independently, hydrogen, or a hydrocarbon residue, optionally being substituted and optionally containing heteroatoms, or groups R and B are joined together to form a ring,

n is an integer equal to the (valency of B minus 2), and \mathbb{R}^1 is a mono-anionic group, and

- b) an activator.
- 20 2. A catalyst system according to claim 1 wherein said group B consists of carbon or silicon,
 - Ar is phenyl, optionally substituted or being part of a larger aromatic entity,
- R¹ is a halide, or mono-anionic hydrocarbon residue optionally containing heteroatoms, and
 - n is 2, then R is a mono-anionic hydrocarbon residue, optionally containing heteroatoms, or
 - n is 1, then R is a di-anionic hydrocarbon residue, optionally containing heteroatoms.

30

- 3. A catalyst system according to claims 1 or 2 in which Ar is a phenyl group, substituted or not at the meta-or paraposition,
- B is based on a carbon atom,
- n is 2, then groups R are, independently, methyl, or ethyl; or
 - n is 1, then group R is = CH_2 , or forms when R is C_4H_8 or C_5H_{10} together with group B a dianionic cyclic group

Cp is C_5H_4 or C_5H_3 (SiMe₃), and R^1 is chlorine, methyl, or benzyl.

10

15

- 4. A catalyst system according to any of the claims 1 to 3wherein said catalyst complex is supported on a carrier.
 - 5. A catalyst system according to any of the claims 1 to 4 wherein said activator is methylalumoxane, a salt of a non-coordinating anion, or a Lewis acid capable of abstracting an anion from said transition metal complex.
 - 6. A catalyst system according to claims 4 and 5 wherein the activator is methylalumoxane and the molar ratio of Ti:Al is from 1:100 to 1:1000.

7. A catalyst system according to any of the claims 1 to 6, wherein said catalyst system further comprises a scavenger.

- 8. A process to trimerize olefinic compounds, which comprises
 carrying out said trimerization in the presence of a catalyst system
 according to any of the preceding claims under trimerization
 conditions.
- 9. A process according to claim 8, wherein said olefin is selected from C_2 - C_{20} olefins or mixtures of two or more of these olefins.

INTERNATIONAL SEARCH REPORT

onal Application No NL 01/00149

			NL 01/	/ UU149	
A. CLASSII IPC 7	FICATION OF SUBJECT MATTER C07C2/32 B01J31/22				
According to	o International Patent Classification (IPC) or to both national class	sification and IPC			
	SEARCHED				
Minimum do IPC 7	cumentation searched (classification system followed by classifi $C07C-B01J$	cation symbols)			
Documentat	tion searched other than minimum documentation to the extent th	al such documents are incl	luded in the fields se	earched	
	lata base consulted during the international search (name of data ternal, WPI Data, CHEM ABS Data	a base and, where pradica	ıl, search terms used		
C. DOCUM	ENTS CONSIDERED TO BE RELEVANT				
Category °	Citation of document, with indication, where appropriate, of the	e relevant passages		Relevant to claim No.	
A	EP 0 608 447 A (PHILLIPS PETROUTED A August 1994 (1994-08-03) cited in the application claims 20-24	8,9			
X	SASSMANNSHAUSEN J ET AL: "HALF COMPLEXES OF TITANIUM AND ZIRCO PENDANT PHENYL SUBSTITUENTS. THE OF ANSA-ARYL COORDINATION ON THEPOLYMERISATION ACTIVITY OF HALF-SANDWICH CATALYSTS" JOURNAL OF ORGANOMETALLIC CHEMI ELSEVIER-SEQUOIA S.A. LAUSANNE vol. 592, 1999, pages 84-94, XI ISSN: 0022-328X cited in the application table 1	ONIUM WITH HE INFLUENCE ISTRY, CH,		1-7	
X Furt	ther documents are listed in the continuation of box C.	X Patent family	y members are listed	lin annex.	
Special ca A' docume consid E' earlier filling of L' docume which citatio O' docume other P' docume later t Date of the	altegories of cited documents: and defining the general state of the art which is not dered to be of particular relevance document but published on or after the international date ent which may throw doubts on priority claim(s) or a is cited to establish the publication date of another on or other special reason (as specified) hent referring to an oral disclosure, use, exhibition or means sent published prior to the international filing date but than the priority date claimed. 2 November 2001	*T* later document pu or priority date ai cited to understal invention *X* document of partiticannot be consictively an invention *Y* document of partiticannot be consisted document is comments, such cominities and comments, such cominities and countered in the art. *&* document members.	cument of particular relevance; the claimed invention annot be considered novel or cannot be considered to volve an inventive step when the document is taken alone cument of particular relevance; the claimed invention annot be considered to involve an inventive step when the ocument is combined with one or more other such docuents, such combination being obvious to a person skilled the art. cument member of the same patent family at the of mailing of the international search report		
	mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized office	r		

INTERNATIONAL SEARCH REPORT

tional Application No

		PCI/NL UI	
	stion) DOCUMENTS CONSIDERED TO BE RELEVANT		Colourat to states to
Category °	Citation of document, with indication, where appropriate, of the relevant passages		Relevant to claim No.
A	WO 94 25416 A (SHELL INT RESEARCH) 10 November 1994 (1994-11-10) page 2, line 14 -page 3, line 4		8,9
		·	
	, "Bayer"		

INTERNATIONAL SEARCH REPORT

nformation on patent family members

tional Application No

							· · ·	
	Patent docume cited in search re		Publication date		Patent family member(s)		Publication date	
	EP 0608447	7 A	03-08-1994	AU	650808	A1	30-06-1994	
				· CA	2087578	A1	20-07-1994	
j				CZ	9300088	A3	17-08-1994	
				JP	3188335	B2	16-07-2001	
				JP	6239920	Α	30-08-1994	
				NO	930340	Α	02-08-1994	
				. EP	0608447	A1	03-08-1994	
	WO 942541	 6 A	10-11-1994	AU	683060	B2	30-10-1997	
				AU	6650394	Α	21-11-1994	
				BR	9406460	Α	30-01-1996	
Ī				CA	2161664	A1	10-11-1994	
				CN	1121704	A,B	01-05-1996	
Ì				CZ	9502826	A3	15-05-1996	
				DE	69405222	D1	02-10-1997	
1				DE	69405222	T2	02-01-1998	
				DK	696263	T3	29-09-1997	
			. نيو	WO	9425416	A1	10-11-1994	
				EP	0696263	A1	14-02-1996	
				FΙ	955104	Α	26-10-1995	
				JР	8509518	T	08-10-1996	
				NO	954292	Α	26-10-1995	
1								